



PRODUCT DATA SHEET

ROADSAVER 515

PART NO. 34515




JANUARY 2008

420 N. Roosevelt Ave. • Chandler AZ 85226
 1-800-528-8242 • (602) 276-0406 • FAX (480) 961-0513
 www.crafco.com

READ BEFORE USING THIS PRODUCT

GENERAL Crafco RoadSaver 515 is a hot-applied asphalt based product used to seal and fill cracks and joints in asphalt and portland cement concrete pavements in moderate to cold climates. RoadSaver 515 is supplied in solid form which when melted and properly applied forms a highly adhesive and flexible compound that resists cracking in the winter and resists flow in the summer. RoadSaver 515 is used in highway, street, and airfield pavements and is applied to pavement cracks and joints using either pressure feed melter applicators or pour pots. At application temperature, RoadSaver 515 is a free flowing, self-leveling product. RoadSaver 515 does not contain any ground cured rubber scrap. The unique formulation of RoadSaver 515 reduces stress buildup during extension at low temperatures which improves long term performance. RoadSaver 515 has been a top performing quality Crafco product for over 20 years and has achieved the **CERTIFIED PERFORMANCE** designation. VOC = 0 g/l

USAGE GUIDELINES RoadSaver 515 pavement temperature performance limits are 64-28 for crack sealing and 64-34 for crack filling. Usage recommendations are shown in Crafco pavement temperature grade charts shown at the right. Refer to Crafco Product Selection Procedures to determine sealant or filler use and pavement temperature grades.



SPECIFICATION CONFORMANCE RoadSaver 515 meets requirements of state modified AASHTO M173 specifications, and exceeds requirements of ASTM D6690 (AASHTO M324), Type I (formerly ASTM D1190, AASHTO M173), and Federal Specification SS-S-164.

Test

Cone Penetration, 77°F (25°C)
 Flow, 140°F (60°C)
 Softening Point
 Resilience, 77°F (25°C)
 Ductility, 77°F (25°C) (ASTM D113)
 Bond, 0°F (-18°C), 100% ext. 1/2" (12.7mm) thick specimen
 Impact, 0°F (-18°C)
 Compression Recovery
 Minimum Application Temperature
 Maximum Heating Temperature

Modified AASHTO M173 Limits

50-90
 0.5 cm max.
 176°F (80°C) min.
 25-60%
 40 cm min.
 Pass 5 cycles
 Pass
 0.40 min.
 380°F (193°C)
 400°F (204°C)



*For details go to Crafco.com

INSTALLATION The unit weight of RoadSaver 515 is 9.9 lbs. per gallon (1.19 kg/L) at 60°F (15.5°C). Prior to use, the user must read and follow Installation Instructions for Hot-Applied RoadSaver, PolyFlex, Parking Lot and Asphalt Rubber Products to verify proper product selection, heating methods, pavement preparation procedures, application geometry, usage precautions and safety procedures. These instructions are provided with each pallet of product.

PACKAGING Packaging consists of individual boxes of product which are palletized into shipping units. Boxes contain a non-adherent film which permits easy removal of the product. Each pallet contains 72 boxes which are stacked in six layers of 12 boxes per layer. The weight of product in each box does not exceed 40 lbs. (18kg) and pallet weights do not exceed 2,880 lbs. (1310kg) Pallets of product are weighed and product is sold by the net weight of product. Product boxes are manufactured from double wall kraft board producing a minimum bursting test certification of 350 psi (241 N/cm²) and using water resistant adhesives. Boxes use tape closure and do not contain any staples. Boxes are labeled with the product name, part number, lot number, specification conformance, application temperatures and safety instructions. Palletized units are protected from the weather using a three mil thick plastic bag, a weather and moisture resistant cap sheet and a minimum of two layers of six month u.v. protected stretch wrap. Pallets are labeled with the product part number, lot number and net weight. Installation Instructions are provided with each pallet in a weather resistant enclosure.

WARRANTY CRAFTCO, Inc. warrants that CRAFTCO products meet applicable ASTM, AASHTO, Federal or State specifications at time of shipment. Techniques used for the preparation of the cracks and joints prior to sealing or filling are beyond our control as are the use and application of the products; therefore, Crafco shall not be responsible for improperly applied or misused products. Remedies against Crafco, Inc., as agreed to by Crafco, are limited to replacing nonconforming product or refund (full or partial) of purchase price from Crafco, Inc. All claims for breach of this warranty must be made within three (3) months of the date of use or twelve (12) months from the date of delivery by Crafco, Inc. whichever is earlier. There shall be no other warranties expressed or implied. **For optimum performance, follow Crafco recommendations for product installation.**